



# NOCTIS UNI Cassis 97

This plain fabric is a classic of our range, it is available in several colors. NOCTIS UNI is a flame retardant and antibacterial blackout fabric. It kills 99% of staphylococcus aureus and klebsiella pneumoniae bacteria (antibacterial action only on Noctis uni color gray flocked back). It does not release any biocidal product into the water when washing the fabric.

## Technical properties



Flame retardant



Antibacterial

**Applications** Roman blinds - Roller blinds - Panel curtains - Lining - Curtains

**Composition** 100% polyester with gray flocked acrylic backing

**Weight** 330 g/m<sup>2</sup> **Width** 200 cm

**Fabric direction** Room high or standard direction **Fitting** ↔ cm ↓ cm

**Maintenance advice**

**Labels** France Terre Textile (R016)

**Minimum order** 1 linear(s) meter(s)

## Technical characteristics

|                 |                                                           |                 |
|-----------------|-----------------------------------------------------------|-----------------|
| Flame retardant | M1 / B1 / IMO PASS                                        |                 |
| Acoustic        | Noise reduction coefficient (NRC) :                       | 0.28            |
|                 | Weighted sound absorption coefficient (a <sub>w</sub> ) : | 0.20            |
|                 | Acoustic absorption class (a <sub>w</sub> ) :             | E               |
| Antibacterial   | Yes                                                       |                 |
| Optical index   | Light reflexion :                                         | 33 %            |
|                 | Light absorption :                                        | 67 %            |
|                 | Light transmission :                                      | 0 %             |
| Thermal index   | Solar reflexion :                                         | 34 %            |
|                 | Solar absorption :                                        | 66 %            |
|                 | Solar transmission :                                      | 0 %             |
|                 | UV transmission :                                         | 0 %             |
|                 | Gtot :                                                    | Gt 46 % Fc 77 % |
| Resilience      | Lightfastness (units Class/8)                             | 3               |
|                 | Pilling                                                   | 5               |
|                 | Dimensional Stability (%)                                 |                 |
|                 | Warp                                                      | -0,5            |
|                 | Weft                                                      | 0               |
|                 | Martindale (Cycles)                                       | 35000           |
|                 | Breaking Elongation                                       |                 |
|                 | Warp                                                      | 20              |
|                 | Weft                                                      | 24              |
|                 | Breaking load (daN)                                       |                 |
|                 | Warp                                                      | 53              |
|                 | Weft                                                      | 63              |



(Headquarters) SOTEXPRO - 510 route de Montchal - 42360 PANISSIÈRES - FRANCE - +33 4 77 27 60 60

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected